

# L'AUTHENTIQUE

PAINTS & INTERIOR

## Chalk paint

### Wood:

#### Painted or unpainted wood

When painting, always ensure a well-ventilated and heated room. The ideal temperature for painting woodwork is 20°C. Do not paint in direct sunlight or an area that is too cold or too humid. Cover floors and surrounding furniture with foil. The surface must be clean, dry and free of grease. We recommend always treating wooden surfaces first with a synthetic oil-based primer. Some tropical woods are greasy, resulting in poor adhesion, oak wood can bleed, causing yellow stains on the surface or old stains may come up. Preferably use a wide, flat brush to paint woodwork with chalk paint.

#### Necessities:

- Cover film
- Protective clothing
- Bucket of water and a cloth
- St Marc or another degreaser
- White spirit and a cloth
- Sandpaper grit 100
- Duster
- Synthetic oil-based primer, possibly by color
- White spirit and a cloth
- A paint roller
- Paint tray
- 2 stir sticks
- Flat brush for chalk paint
- Brush for the oil-based primer
- Chalk paint
- Sealer or polish

1. Cover all floors and furniture with foil
2. Degrease the woodwork with St. Marc or another suitable degreasing product
3. Rinse with clean water and let the woodwork dry thoroughly
4. Lightly sand the surface to open the pores and create adhesion
5. Dust the surface
6. Stir the primer well
7. Carefully pour the synthetic oil-based primer into a paint tray
8. Remove any splashes with a cloth dampened with turpentine
9. Run the roller through the paint and make sure the paint is evenly distributed on the roller
10. Paint the surface and let it dry thoroughly, refer to the label or manual

# L'AUTHENTIQUE

---

## PAINTS & INTERIOR

11. Sand the surface lightly after drying
12. Paint the surface with the chalk paint and let it dry sufficiently, consult the label or manual
13. Paint the second coat and let it dry sufficiently
14. Chalk paint is light washable. If desired, finish a wooden surface with a sealer or floor wax. A sealer or floor wax must harden for at least 2 weeks before it can be polished.